

High Street, Brandon, Suffolk IP27 0AX - Tel: 01842 810678 - Fax: 01842 814602 - E-mail:  
info@lignacite.co.uk - Website: www.lignacite.co.uk  
Meadgate Works, Nazeing, Waltham Abbey, Essex EN9 2PD - Tel: 01992 464441 - Fax: 01992 445713

Project Title: **[Insert project title]**

## **Masonry Specifications**

### **1.2 Common Blockwork**

The concrete blocks to ... (Internal) ... shall be **Lignacite GP SP** produced by **Lignacite Ltd**, tel 01842 810678 or other equal approved.

Category 1 Masonry Units.

Minimum mean compressive strength of: **3.6 N/mm<sup>2</sup>**

Form: **Solid**

Face size: **440 x 215 mm**

Thickness: **140 mm**

Colour: **Medium Grey**

Average density: **1450 kg/m<sup>3</sup>**

Thermal Resistance: **0.177 m<sup>2</sup>K/W**

Mortar mix: **Class M4**

Joint profile: (bucket handle, flush, struck or weathered, recessed)

Bond: (stack, stretcher)

Sound Insulation: **51 RwdB**

Fire Resistance (load bearing): **2 Hrs**